

Nanotechnology and Chitosan Nanoparticles in Veterinary Medicine

AbdulRahman A. Saied

Received: 15 December 2019 Accepted: 5 January 2020 Published: 15 January 2020

Abstract

Nanotechnology is the new interesting field of science that enables us to use agents of extremely tiny sizes below 100 nm in novel applications. Although advent of nanotechnology in veterinary medicine isn't similar as in human medical settings, but this field has been a recently attracted veterinary researcher. Here, we review the recent papers dealt with the uses of nanoparticles in variety of applications in particular chitosan nanoparticles.

Index terms— nanotechnology, veterinary medicine, chitosan nanoparticles, wound healing.

1 Introduction

he skin is the largest organ in our body that provides a protective covering for the body besides its other physiological and defensive functions [1]. One of the most common skin pathologies is wound that defined as any break and disruption of the normal cellular and anatomical or functional continuity of the skin [2,3]. Wound is a multifactorial disorder and it could be caused by physical, chemical, electrical or microbial causes [2]. Returning of skin to normal structure and replacement of destroyed or damaged tissue by newly produced tissue is called wound healing. Wound healing is a physiological and complex process established by four continues and overlapping phases (hemostasis; inflammation; proliferation, and tissue remodeling) [4,5].

There are no lines of demarcation between the four previously mentioned stages that can be detected on the clinical or cellular level. The main goal of wound healing is to speed the recovery and restore the normal anatomical structure and function of the injured part with minimal scarring [6]. These steps involve multiple cellular and molecular events tightly controlled by numerous growthfactors, chemokines, and cytokines. In addition to the dynamic relationship between skin and microbiome (skin flora), that is another major contributor to the outcome of the wound healing process [7]. Signaling networks involving the interleukin (IL) family and growth factors are required to coordinate cell-cell and cell-extracellular matrix (ECM) interactions, that are essential to fully wound healing [8,9].

The program of healing process can be interrupted by numerous factors which are classified into local factors (oxygenation, woundinfection, foreign body, venous sufficiency, wounded part, depth, local tension, and pressure) and systemic factors (age, gender, sex hormones, stress, ischemia, diseases, obesity, medications, alcoholism, smoking, immunocompromised conditions, and nutrition) [10,11], Fig (1). Here in our paper, we highlight the variable applications of nanotechnology in veterinary medicine such as animal production, reproduction, diagnosis and treatment, nanovaccines, drug delivery, Nanosensors, and wound healing. Also, Chitosan nanoparticles were separately discussed.

Nanotechnology is a rapidly developing branch of science that studies the synthesis, structure, and dynamic of the atomic and molecular nanometer (maximum diameter of 100 nm) of nanoparticles [12]. Nanoparticles are synthesized by size reduction using either top-down methods such as milling, high-pressure homogenization and sonication or bottom-up processes such as reactive precipitation and solvent displacement [13]. The size and shape are key determinants to the biological efficiency of nanoparticles, by influencing active substance delivery (carrier circulation), penetrability (either directly through cell membranes or through phagocytosis), and cellular responses (receptor recognition) [14,15]. The convergence of nanotechnology with medicine has been adding new hope in the therapeutic and pharmaceutical fields through a new discipline known as nanomedicine. This is the way for the development of novel materials and for the treatment of several pathologies [16].

2 a) Nanotechnology in Veterinary Medicine

Nanotechnology application in veterinary medicine is still relatively innovative. Recently, the nanoapplications are already used in the veterinary medicine, animal health, production, breeding, reproduction, and nutrition [17], Fig (2).

3 Diagnosis and Treatment

In veterinary medicine, there is little definition of an animal's condition until clinical symptoms are detected. Infection can be substantially spread in the herd until disease is diagnosed. Nanotechnology may be effective method in critical clinical diagnoses because of this property [18].

Biochips can be used for diagnosis of animal diseases. A Biochip (or microarray) is a device typically made of hundreds or thousands of short artificial DNA strands that are accurately deposited on a silicon circuit. Biochips can also be used to trace the source of food and feeds to detect the presence of animal products from different species as a means to locate the source of pathogens a response to public health threats as avian flu and mad cow disease [19]. Using biochips, biological samples such as blood, tissue and semen can be instantaneously analysed and manipulated [20]. Nanoshells can be injected into the animal's to locate tumour cells. The nanoparticles release an attached drug at the tumor site to destroy the cancer cells. [26]. Also it has a role in reduction of aflatoxin as in use of nanosilver which used in treatment of experimental aflatoxicosis in broiler chickens. In other study revealed that supplement of nanosilver to diet containing aflatoxin could diminish the inhibitory effects of aflatoxin [27]. Also, gold nanoparticles and gold-based test strip have been used for the rapid detection of infectious bursal disease (IBD)virus antibodies in chickens[28], foot-and-mouth disease (FMD) virus [29], pathogenic bacteria [30], bluetongue virus [31], specific bacterial contaminants in chicken, such as *S. typhimurium* and *S. enteritidis* [32], antibacterial effect against *Bacillus Calmette-Guérin* (BCG) and *Escherichia coli* [33], haptoglobin in mastitic milk of bovine [34], diagnosis of viral infections in pigs [35], rapid detection of *Mycoplasma suis* in porcine plasma [36], and bacterial toxins [37]. Mastitis is common multifactorial disease that affects high-yielding animals primarily cows and is usually caused by *Staphylococcus*, *Streptococcus*, and *E. coli*, which leads to economic consequences for reducing the yield of milk [38,39]. Zinc oxide nanoparticles (ZnO-NPs) have been found to be effective against bacterial biofilms inside the udder tissue such as *S. aureus* and *E. coli* [40,41]. ZnO-NPs is more sensitive to detect cancer biomarkers and used in diagnostic and therapeutic purposes in common neoplastic conditions of animals such as lymphoma, cutaneous cancer, transmissible venereal tumor, and equine sarcoids [42][43][44].

In experimental studies applied by [45] on recent and infected wound in veterinary field by application of chemical and green synthesized ZnO NPs, they concluded that NPs having excellent antimicrobial healing effect with minimal scarring especially in green synthesized ZnO NPs. Also, Nanoparticles could be used in mass treatments of ectoparasites facilitating the drug-parasite interaction. Nanoparticles are used for improvement of the effectiveness of phytotherapeutic products such as theantiparasitic silver nanoparticles using *Cissusquadrangularis* against *Hippoboscaaculata* and *Rhipicephalus* (*Boophilus*) *microplus* [46]. The nanoshells facilitate the target of the parasite improving the treatment of parasites and it can be useful in the study of host-parasite as biosensors. Nanodevices can allow the diagnostic of parasite in herds allowing veterinarians to suggest a correct health management [47].

4 Nanovaccines

Nanotechnology provides different forms of veterinary nanovaccines such as: recombinant *Bacillus anthracis* spore-based vaccine, influenza virus vaccine, *Helicobacter pylori* vaccine, Tetanus toxoid, Bordetella pertussis vaccine, Rota virus capsid vaccine and Bovine parainfluenza type 3 vaccine. The mucosal immunity is developed following intranasal administration of influenza virus vaccine and both IgG and IgA immune response are developed following the oral administration Bovine parainfluenza type 3 vaccine.

Also chitosan nanoparticles (CS NPs) were prepared with *Leishmania* superoxide dismutase and subcutaneously injected as recombinant *Leishmania* SOD vaccine. Also, intranasal (pneumococcal antigen A vaccine and *Streptococci equi* vaccine) or pulmonary (TB vaccine) vaccines were nano-based. Also, gold nanoparticle-based vaccine were developed against FMD, Newcastle disease, influenza virus, or herpes simplex virus 2, and also vaccines of African horse sickness virus (AHSV) [48][49][50].

5 Drug Delivery

The nanoparticles play an important role in drug delivery as they can carry drug and genes to the target site. The drug delivery systems have important effects on absorption, distribution, and excretion rate of drugs or other substances in the body [6]. Liquid vitamins that were prepared by nanotechnology are available for poultry feed and their nanosized are designed to pass through the gastrointestinal tract and deliver the vitamins or other nutrients directly in the bloodstream and therefore increase their bioavailability. NPs mask undesired tastes and improve the nutrient dispersibility and durability of the feed. In addition, they decrease the need to use preservatives [51]. In animals, smart drug delivery systems allow antibiotic use in amounts less than possible. Also, smart delivery systems can perform processes such as its ability to decide the regulation in the process of

104 delivery of drug or its ability to make the drug addition according to the need, and the perception of chemicals
105 in the site. Smart delivery system decrease the antibiotic usage and the treatment cost in farms [52].

106 **6 Nanosensors**

107 Nanosensors are miniature devices that can be used for diagnosis of biological material or tissue samples [53].
108 It has been used in several biomedical applications in veterinary medicine including animal health for diagnosis
109 of some microbial pathogens diseases [54,55] and for animal production, especially the delivery of controlled
110 quantities of drugs into breeding animal beverages. Nanosensors used for prevention of bovine tuberculosis [54]
111 and early diagnosis of subclinical Ketosis (SCK) that is essential for management of dairy cattle health [56].
112 Detection of *Mycobacterium bovis* using nanosensors in infected cattle via breath allowed for real-time cattle
113 monitoring [57]. In addition, the sensors can be used to measure body temperature, antibiotic detection, detect
114 their sweat constituents, observation of behavior, movement, and stress via the implantation on animals [55].

115 **7 Animal production and Food sector**

116 By experimental studies applied by [58] on New Zealand White rabbits fed on nanoparticles; they showed increased
117 weight gain at the fattening period. Similar beneficial production effects have been reported by [59] and [60] in
118 chicken experiments. As the excellent results to an additive which improves the sanitary status of animals. So,
119 the beneficial effect of nanoparticles used in animal production was most frequently observed in such parameters
120 as weight gain, average daily gain, or improvement of the feed conversion rate (FCR) value [61]. As well, the
121 nanomaterials that have been digested and shed in the feces can be used for fertilization in pastoral soil.

122 Nowadays, the nanomaterials are used for meat production as ingredients or additives in the food. They
123 enhance the taste and reduce the use of fat, salt, sugar, and preservatives. Reducing the salt level is especially
124 important and presents a great challenge for meat industry because in spite of advantages, use of salt consequently
125 increased risk of cardiovascular disease since it is linked to hypertension [62].

126 **8 Animal reproduction**

127 Management of breeding is an expensive and time-consuming problem for dairy and swine farmers [19]. There
128 are various applications of nanotechnology in the field of animal reproduction which optimize the general
129 reproductive performance at its different stages starting from the diagnosis and treatment of reproductive
130 disorders and detection of estrus till managing reproductive problems such as retained placenta [63]. Also,
131 the NPs can also be used for sustained release of reproductive hormones [64].

132 Currently, Nanosensors also used to diagnose genital tract infectious diseases, metabolic and hormonal
133 disorders, and even for the detection of estrus [65,66]. Similarly, a nanotube implanted under the skin, it is
134 bind and detects the estradiol antibody at the time of oestrus by near infrared fluorescence and the change in
135 level of estradiol in the blood can be measured [19].

136 **9 b) Chitosan Nanoparticles (CS NPs)**

137 Chitosan Nanoparticles (CS NPs) is an excellent example of nanomaterials which included in all stages of wound
138 healing [67]. CS NPs showed an increased activity than its parent chitosan [68] due to its increased surface
139 to volume ratio [69]. Chitosan is a natural and biodegradable polysaccharide composed of β -1,4 linked N-
140 acetylglucosamine and derived from the alkaline deacetylation of chitin which is the principal component of
141 the cell walls of some fungi and the exoskeleton of insects, crustaceans [70,71], mollusks [72], yeast or green algae
142 [73].

143 **10 Synthesis**

144 CS NPs consists of three functional groups, including an amino group and primary and secondary hydroxyl groups.
145 CS NPs can be cross-linked with glutaraldehyde, glyoxal, and terephthaldehyde, producing hydrogels that can
146 be used in different applications such as organ transplants, restoring organ function, gene delivery, and targeted
147 therapy [74,75]. so, chitin and chitosan are manufactured commercially in large scale [76]. In its crystalline
148 form, chitosan is normally insoluble in an aqueous solution above pH 7; however, in diluted acids (pH 6.0),
149 the protonated free amino groups on glucosamine facilitate solubility of the molecule. Chitosan preparations of
150 various molecular weights (50-2,000 kDa), degrees of deacetylation (30-95%), and further molecular derivatization
151 patterns allow extensive adjustment of mechanical and biological properties [77].

152 CS NPs can be synthesized using either "bottom-up" or "top-down" approaches and/or a combination of both
153 procedures [78]. CS NPs are synthesized through numerous "bottom-up" approaches such as polymerization of CS
154 with methacrylic acid (PMAA) to make CH-PMAA NPs, or through a reverse micelle medium or microemulsion
155 methods [79]. Topdown approaches such as milling, high-pressure homogenization, and ultra-sonication are also
156 applied for the synthesis of these nanomaterials [80]. Many methods have been employed for the syntheses of
157 CS NPs, but five methods are presently available. They are ionotropic gelation, microemulsion, emulsification
158 solvent diffusion, polyelectrolyte complex, and reverse micelle method [81], Fig (3). Out of this, the most widely

159 used methods are ionotropic gelation and polyelectrolyte complex. These methods are simple and do not apply
160 high shear force or use organic solvents [82].

161 11 Biomedical applications

162 Chitosan nanoparticles have great commercial value due to its high nitrogen content and other physiochemical
163 properties like biocompatibility, adsorptive ability [69], biodegradable [72], anticholesterolemic, fungistatic,
164 noncarcinogenic, remarkable affinity to proteins, stimulation of healing, tissue engineering scaffolds, and drug
165 delivery [83][84][85]. In addition to, hemostatic activity, anti-infectious activity, property to accelerate wound
166 healing [86], allergenicity, and bioactivity make it a very attractive substance for diverse applications as a
167 biomaterial in the biomedical, food, and chemical industries [87,88]. Other chitosan properties are low toxicity,
168 availability, low cost, permeability to oxygen, and ease of chemical modification [70,89,90]. The biodegradation
169 rate of chitosan samples is the highest at a temperature of 36°C and is characterized by a relatively prolonged
170 induction period, which is shorter at higher temperatures. The smaller the molecular weight of chitosan, the
171 shorter the induction period [91].

172 12 Drug Delivery

173 Separated reports are available on the use of combinations of antibiotics and chitosan and its derivatives as
174 antimicrobials. Decker et al. proposed a synergistic chlorhexidine/chitosan combination for improved anti-plaque
175 strategies [92]. Tobramycin is one of the antibiotics which is reported to show synergistic action with chitosan
176 in planktonic culture of *Pseudomonas aeruginosa* [93]. Bioadhesive and antimicrobial properties of chitosan and
177 its derivatives are effective in antimicrobial drug delivery control, release of Chlorhexidine and Nystat in oral
178 preparations [94,95], release of ampicillin [96], drug delivery system for Ofloxacin [97] in ophthalmic preparations,
179 and gastrointestinal-release preparations for Tobramycin sulfate [98].

180 13 Antimicrobial and antifungal activities

181 CS NPs are present in many forms such as beads, powders, gels, sponges, tubes, fibers, and films [99][100][101],
182 hydrogel [102], and biofilm [103]. These forms facilitate the antibacterial and wound-healing activity of CS
183 NPS. Chitosan nanoparticles were shown to have significant bactericidal effects on different types of bacteria
184 and no cytotoxic effect on mouse fibroblast cells [104]. Their antimicrobial effects against a broad range of
185 gram positive and gram-negative bacteria as well as fungi were reported [105][106][107]. Archana, D., et al.,
186 reported in an experiment on a wound in rats the antimicrobial and wound-healing activity of chitosan [67].
187 Although several studies have shown that chitosan exhibited higher antibacterial activity against grampositive
188 bacteria than gram-negative bacteria, while some other studies have shown that gram-negative bacteria as more
189 susceptible than gram-positive [108,109], many works have demonstrated that there is no significant difference
190 between antibacterial activity and bacterial species [110].

191 Studies have reported the antibacterial activity of CHNP against *Escherichia coli*, *Staphylococcus aureus*,
192 *Streptococcus mutans*, *Salmonella typhimurium*, *Salmonella choleraesuis*, and *Pseudomonas aeruginosa* [107,111].
193 Antifungal activity of CHNP has also been reported against *Aspergillus niger*, *Fusarium solani*, *Rhizoctonia solani*,
194 *Collectotrichum gloeosporioides*, *Candida albicans* [68,112]. Chitosan's antibacterial efficacy also depends on
195 multiple, factors both intrinsic and extrinsic. Intrinsic parameters comprise the molecular weight and degree
196 of deacetylation of parent chitosan, nanoparticle size, and concentration. The extrinsic factors involve pH,
197 temperature, reactive time and so on [113].

198 The CS NPS size is an important factor which affects its antimicrobial activity, as the decrease in size at
199 lower concentrations is due to decreased viscosity causing better solubility of chitosan in acetic acid solution and
200 resulting in better action of chitosan [114].

201 However, deacetylation degree, positive charge content, and other factors including molecular weight can affect
202 the antibacterial activities of chitosan [115], as the molecular weight has a stronger effect on the antimicrobial
203 activity compared to the degree of acetylation [108,116,117]. It has been reported that decreasing the molecular
204 weight of chitosan may increase its binding affinity to the membrane due to improved mobility, attraction, and
205 ionic interaction [118], though a proper antibacterial activity can be obtained only when the molecular weight
206 is larger than 10 kDa [119]. In acid, the antimicrobial activity was shown to increase with increasing molecular
207 weight [116], while the antimicrobial activity changed at pH 7.0 [115].

208 The most prevalent proposed antibacterial activity of chitosan is by binding to the negatively charged bacterial
209 cell wall causing disruption of the cell thus altering the membrane permeability [120,121], followed by attachment
210 to DNA causing inhibition of DNA replication and subsequently cell death [121]. Another possible mechanism
211 is that chitosan acts as a chelating agent that selectively binds to trace metal elements causing toxin production
212 and inhibiting microbial growth [122]. For instance, chitosan composites have shown antiviral activity against
213 H1N1 influenza A virus [123] and Human cytomegalovirus (HCMV) strain AD-169 [123,124].

214 14 Wound healing

215 The application of nanotechnology in the field of wound healing gave way to the manufacture and innovation
216 of many bandages, which in turn speed up healing with the least possibility of scarring. [16]. From our point

217 of view, the good selection of suitable nanomaterials for different wound types can play the main role in wound
218 healing and tissue remodeling. The nanomaterials used in wound healing are classified into two categories: (1)
219 nanomaterials that exhibit intrinsic properties beneficial for wound treatment and (2) nanomaterials included
220 in drug delivery [125,126]. An experimental study performed by Chandika, P., et al [128] documented that
221 chitosan increased wound healing rates in mice. N-acetyl glucosamine (NAG) present in chitin and chitosan is a
222 major component of dermal tissue which is essential for repair of scar tissues [129]. Chitosan's positive surface
223 charge enables it to effectively support cell growth [130] and promotes surface-induced thrombosis and blood
224 coagulation. Free amino groups which are present on the chitosan membrane surface may form polyelectrolyte
225 complexes with acidic groups of the cellular elements of blood [86]. Chitosan promotes the dermal regeneration
226 during skin reconstruction by regulating the deposition and accelerating the arrangement of thin collagen fibers.
227 It also modulates fibroblast activation, sustaining the regeneration of the extracellular matrix while stimulating
228 cell proliferation and migration (i.e. the formation of granulation tissue) and enhancing wound healing [131].

229 Natural products-derived biomaterials can provide materials with greater complexity and composition, and
230 in order to mimic the extracellular matrix (ECM) conditions of the wound and to provide a scaffold for the
231 fibroblasts for collagen deposition, ECMbased therapies have gained popularity [132].

232 Studies suggest that chitin and chitosan promote the migration of polymorphonuclear and mononuclear cells
233 and accelerate the reformation of connective tissue and angiogenesis (necessary for the arrival of repair cells such
234 as fibroblast) [133]. In recent studies, chitosan has been used to deliver bioactive molecules, basic fibroblast
235 growth factor [86] and human epidermal growth factor [134] were encapsulated in this biomaterial; electrospun
236 nonwoven nanofibrous hybrid mats based on chitosan and poly[(L-lactide)-co-(D,L-lactide)] were produced; [135]
237 chitosan dressing incorporating a procoagulant (polyphosphate) and an antimicrobial (silver); [85] and chitosan
238 acetate bandages were used as a topical antimicrobial dressing for infected burns [83].

239 15 II.

240 16 Conclusion

241 Nanotechnology is a rapidly developing branch of science that could be applied in various aspects with different
242 actions. Although advent of nanotechnology in veterinary medicine isn't similar as in human medical settings,
243 but this field has been recently attracted veterinary researchers. We conclude that the field of nanotechnology
244 in veterinary medicine is a promising field in different disciplines; surgery, pharmacology, vaccinology ... etc. 17.
245 ??anuja

246 Figure Legends

247 ¹





Figure 1:



1

Figure 2: Fig. (1):



3

Figure 3: Fig. (3):

.1 Conflict of interest

248 No conflict of interest.

249 [Biomacromolecules ()] , *Biomacromolecules* 2003. 4 p. .

251 [Goy et al. ()] , R Goy , D Britto , O Assis . *A Review of the Antimicrobial Activity of Chitosan. Polimeros-ciencia*
252 *E Tecnologia -POLIMEROS* 2009. 19.

253 [Nanotechnologies in Optics and Electronics ()] , *Nanotechnologies in Optics and Electronics* 2010. 46 p. .

254 [Biosensors bioelectronics ()] , *Biosensors & bioelectronics* 2013. 55 p. .

255 [Zhang ()] , A Zhang . *Chitosan Coupling Makes Microbial Biofilms Susceptible to Antibiotics. Scientific Reports*
256 2013. 3 (1) p. 3364.

257 [Environmental Chemistry Letters ()] , *Environmental Chemistry Letters* 2017.

258 [Environmental Science and Pollution Research ()] , *Environmental Science and Pollution Research* 2020. 27
259 (16) p. .

260 [Ding ()] ‘A highly sensitive detection for foot-and-mouth disease virus by gold nanoparticle improved immuno-
261 PCR’. Y.-Z Ding . *Small (Weinheim an der Bergstrasse* 2011. 2011. 8 (7) p. . (Virology journal)

262 [Decker ()] ‘A synergistic chlorhexidine/ chitosan combination for improved antiplaque strategies’. E M Decker .
263 *Journal of periodontal research* 2005. 40 p. .

264 [El-Sayed and Kamel] *Advanced applications of nanotechnology in veterinary medicine*, A El-Sayed , M Kamel .

265 [Kishen ()] ‘An Investigation on the Antibacterial and Antibiofilm Efficacy of Cationic Nanoparticulates for Root
266 Canal Disinfection’. A Kishen . *Journal of endodontics* 2009. 34 p. .

267 [Zhou ()] ‘Antibacterial activities of gold and silver nanoparticles against Escherichia coli and bacillus Calmette-
268 Guérin’. Y Zhou . *Journal of nanobiotechnology* 2012. 10 p. .

269 [Li et al. ()] *Antibacterial activity and mechanism of chitosan with ultra high molecular weight. Carbohydrate*
270 *Polymers*, J Li , Y Wu , L Zhao . 2016. 148 p. .

271 [Benhabiles ()] ‘Antibacterial activity of chitin, chitosan and its oligomers prepared from shrimp shell waste’. M
272 S Benhabiles . *Food Hydrocolloids* 2012. 29 (1) p. .

273 [Van Toan et al. ()] ‘Antibacterial Activity of Chitosan on Some Common Food Contaminating Microbes’. N
274 Van Toan , T Hanh , P Thien . *The Open Biomaterials Journal* 2013. (4) p. .

275 [No ()] *Antibacterial activity of chitosans and chitosan oligomers with different molecular weights. International*
276 *journal of food microbiology*, H K No . 2002. 74 p. .

277 [Tamara ()] ‘Antibacterial Effects of Chitosan/ Cationic Peptide Nanoparticles’. F R Tamara . *Nanomaterials*
278 2018. 8 (2) p. 88.

279 [Ing ()] ‘Antifungal Activity of Chitosan Nanoparticles and Correlation with Their Physical Properties’. L Y Ing
280 . *International Journal of Biomaterials* 2012. 2012. p. 632698.

281 [Chávez De Paz ()] ‘Antimicrobial Effect of Chitosan Nanoparticles on Streptococcus mutans’. L E Chávez De Paz . *Biofilms. Applied*
282 *and Environmental Microbiology* 2011. 77 (11) p. .

284 [Kong ()] ‘Antimicrobial properties of chitosan and mode of action: A state of the art review’. M Kong .
285 *International Journal of Food Microbiology* 2010. 144 (1) p. .

286 [Divya ()] *Antimicrobial properties of chitosan nanoparticles: Mode of action and factors affecting activity. Fibers*
287 *and Polymers*, K Divya . 2017. 18 p. .

288 [Mori ()] ‘Antiviral activity of silver nanoparticle/chitosan composites against H1N1 influenza A virus’. Y Mori
289 . *Nanoscale Research Letters* 2013. 8 (1) p. 93.

290 [Ahmadi and Ahmadi ()] ‘Application of Different Levels of Silver Nanoparticles in Food on the Performance
291 and Some Blood Parameters of Broiler Chickens’. M Ahmadi , J Ahmadi . *World Applied Sciences Journal*
292 2009. 7 p. .

293 [Korystov ()] *Avermectins inhibit multidrug resistance of tumor cells*, Y N Korystov . 2004. 493 p. .

294 [Kenawy ()] ‘Biologically Active Polymers: Modification and Anti-microbial Activity of Chitosan Derivatives’.
295 E.-R Kenawy . *Journal of Bioactive and Compatible Polymers* 2005. 20.

296 [Singh and Ray] ‘Biomedical Applications of Chitin, Chitosan, and Their Derivatives’. D Singh , A Ray . *Journal*

297 [Badawy and Rabea ()] ‘Biopolymer Chitosan and Its Derivatives as Promising Antimicrobial Agents against
298 Plant Pathogens and Their Applications in Crop Protection’. M Badawy , E Rabea . *International Journal*
299 *of Carbohydrate Chemistry Article ID* 2011. Hindawi Publishing Corporation. p. 460381.

300 [Nayantara and Kaur ()] ‘Biosynthesis of nanoparticles using eco-friendly factories and their role in plant
301 pathogenicity: a review’. P Nayantara , Kaur . *Biotechnology Research and Innovation* 2018. 2 (1) p. .

- 302 [Dobson ()] *Canine neoplasia in the UK: Estimates of incidence rates from a population of insured dogs. The*
303 *Journal of small animal practice*, J Dobson . 2002. 43 p. .
- 304 [Einbu and Vårum ()] ‘Characterization of Chitin and Its Hydrolysis to GlcNAc and GlcN’. A Einbu , K M
305 Vårum . *Biomacromolecules* 2008. 9 (7) p. .
- 306 [Roberts ()] *Chitin chemistry*, G A F Roberts . 1992. London: Macmillan.
- 307 [Muzzarelli ()] *Chitin nanofibrils/chitosan glycolate composites as wound medicaments. Carbohydrate Polymers*,
308 R Muzzarelli . 2007. 70 p. .
- 309 [Dai ()] ‘Chitosan Acetate Bandage as a Topical Antimicrobial Dressing for Infected Burns’. T Dai . *Antimicrobial*
310 *Agents and Chemotherapy* 2009. 53 (2) p. .
- 311 [Champer ()] *Chitosan against cutaneous pathogens*, J Champer . 2013. AMB Express. 3 p. .
- 312 [Aksungur ()] ‘Chitosan delivery systems for the treatment of oral mucositis: in vitro and in vivo studies’. P
313 Aksungur . *Journal of controlled release: official journal of the Controlled Release Society* 2004. 98 (2) p. .
- 314 [Li ()] *Chitosan kills Escherichia coli through damage to be of cell membrane mechanism. Carbohydrate Polymers*,
315 X.-F Li . 2010. 79 p. .
- 316 [Wang ()] ‘Chitosan nanoparticles loaded hydrogels promote skin wound healing through the modulation of
317 reactive oxygen species’. T Wang . *Nanomedicine, and Biotechnology* 2017. 46 p. . (Artificial Cells)
- 318 [Wang ()] *Chitosan nanoparticles loaded hydrogels promote skin wound healing through the modulation of reactive*
319 *oxygen species. Artificial cells, nanomedicine, and biotechnology*, T Wang . 2017. 46 p. .
- 320 [Koilparambil and Shanavas] *Chitosan nanoparticles preparation and applications*, D Koilparambil , J Shanavas
321 .
- 322 [Divya and Jisha ()] ‘Chitosan nanoparticles preparation and applications’. K Divya , M S Jisha . *Environmental*
323 *Chemistry Letters* 2018. 16 (1) p. .
- 324 [Tiyaboonchai] ‘Chitosan Nanoparticles: A Promising System for Drug Delivery’. W Tiyaboonchai . *Naresuan*
325 *University Journal: Science and Technology (NUJST)* 2013 (3) p. .
- 326 [Anal and Stevens ()] ‘Chitosan-alginate multilayer beads for controlled release of ampicillin’. A Anal , W Stevens
327 . *International journal of pharmaceutics* 2005. 290 p. .
- 328 [Mekahlia and Bouzid ()] ‘Chitosan-Copper (II) complex as antibacterial agent: synthesis, characterization and
329 coordinating bond-activity correlation study’. S Mekahlia , B Bouzid . *Physics Procedia* 2009. 2 (3) p. .
- 330 [Motwani ()] ‘Chitosan-sodium alginate nanoparticles as submicroscopic reservoirs for ocular delivery: formu-
331 lation, optimisation and in vitro characterisation’. S K Motwani . *European journal of pharmaceutics and*
332 *biopharmaceutics: official journal of Arbeitsgemeinschaft fur Pharmazeutische Verfahrenstechnik e.V* 2008.
333 68 (3) p. .
- 334 [Saragusty and Arav ()] ‘Current progress in oocyte and embryo cryopreservation by slow freezing and vitrifica-
335 tion’. J Saragusty , A Arav . *Reproduction* 2010. 141 p. .
- 336 [Li ()] ‘Cytotoxicity and biocompatibility evaluation of N,O-carboxymethyl chitosan/oxidized alginate hydrogel
337 for drug delivery application’. X Li . *International journal of biological macromolecules* 2012. 50 (5) p. .
- 338 [Sekhon ()] *Daru : journal of Faculty of Pharmacy*, B S Sekhon . 2012. 20 p. . Tehran University of Medical
339 Sciences (Drug-drug co-crystals)
- 340 [Peled ()] ‘Detection of volatile organic compounds in cattle naturally infected with Mycobacterium bovis’. N
341 Peled . *Sensors and Actuators B: Chemical* 2012. p. .
- 342 [Katas and Alpar ()] ‘Development and characterisation of chitosan nanoparticles for siRNA delivery’. H Katas
343 , H O Alpar . *Journal of Controlled Release* 2006. 115 (2) p. .
- 344 [Ong ()] ‘Development of a chitosan-based wound dressing with improved hemostatic and antimicrobial proper-
345 ties’. S.-Y Ong . *Biomaterials* 2008. 29 (32) p. .
- 346 [Wang ()] ‘Development of a gold nanoparticle-based oligonucleotide microarray for simultaneous detection of
347 seven swine viruses’. X Wang . *Journal of virological methods* 2013. 191.
- 348 [Ribeiro ()] *Development of a new chitosan hydrogel for wound dressing. Wound repair and regeneration*, M P
349 Ribeiro . 2009. 17 p. .
- 350 [Tan ()] ‘Development of an immunosensor assay for detection of haptoglobin in mastitic milk’. X Tan . *Veterinary*
351 *Clinical Pathology* 2012. p. 41.
- 352 [Meng] *Development of colloidal goldbased immunochromatographic assay for rapid detection of Mycoplasma suis*
353 *in porcine plasma*, K Meng .
- 354 [Krishna Sailaja et al. ()] ‘Different technique used for the preparation of nanoparticles using natural polymers
355 and their application’. A Krishna Sailaja , P Amareshwar , P Chakravarty . *Int. J. Pharm. Sci* 2011. p. .

- 356 [Mizuno ()] ‘Effect of chitosan film containing basic fibroblast growth factor on wound healing in genetically
357 diabetic mice’. K Mizuno . *Journal of biomedical materials research. Part A* 2003. 64 p. .
- 358 [Ikinci ()] ‘Effect of chitosan on a periodontal pathogen Porphyromonas gingivalis’. G Ikinci . *International journal
359 of pharmaceutics* 2002. 235 p. .
- 360 [Moustafa ()] ‘Effect of Dietary Nanosilver on Broiler Performance’. K E Moustafa . *International Journal of
361 Poultry Science* 2015. 14 p. .
- 362 [Pastar ()] ‘Epithelialization in Wound Healing: A Comprehensive Review’. I Pastar . *Advances in wound care*
363 2014. (3) p. .
- 364 [Borzacchiello and Corteggio ()] ‘Equine sarcoid: State of the art’. G Borzacchiello , A Corteggio . *Ippologia*
365 2009. 20 p. .
- 366 [Jalal ()] ‘Escherichia coli signal peptidase recognizes and cleaves the signal sequence of xylanase from a newly
367 isolated Bacillus subtilis strain R5’. A Jalal . *Biochemistry (Moscow)* 2011. 76 (3) p. .
- 368 [Santhoshkumar ()] *Evaluation of stem aqueous extract and synthesized silver nanoparticles using Cissus quad-*
369 *rangularis against Hippobosca maculata and Rhipicephalus (Boophilus) microplus. Experimental parasitology,*
370 T Santhoshkumar . 2012. 132 p. .
- 371 [Farahpour ()] *Evaluation of the wound healing activity of an ethanolic extract of Ceylon cinnamon in mice.*
372 *Veterinárni medicína*, M Farahpour . 2012. 57 p. .
- 373 [Arun et al. ()] *Evaluation of wound healing, antioxidant and antimicrobial efficacy of Jasminum auriculatum*
374 *Vahl. leaves. Avicenna journal of phytomedicine*, M Arun , S Satish , P Anima . 2016. 6 p. .
- 375 [Guo and Dipietro ()] ‘Factors affecting wound healing’. S Guo , L A Dipietro . *Journal of dental research* 2010.
376 89 (3) p. .
- 377 [Gao et al. ()] ‘Functional enhancement of chitosan and nanoparticles in cell culture, tissue engineering, and
378 pharmaceutical applications’. W Gao , J C K Lai , S W Leung . *Frontiers in physiology* 2012. 3 p. .
- 379 [Ghorbani ()] *In vitro synergy of antibiotic combinations against planktonic and biofilm Pseudomonas aeruginosa.*
380 *GMS hygiene and infection control*, H Ghorbani . 2017. 12 p. .
- 381 [Archana ()] *In vivo evaluation of chitosan-PVP-titanium dioxide nanocomposite as wound dressing material.*
382 *Carbohydrate polymers*, D Archana . 2013. 95 p. .
- 383 [Archana ()] *In vivo evaluation of chitosan-PVP-titanium dioxide nanocomposite as wound dressing material.*
384 *Carbohydrate polymers*, D Archana . 2013. 95 p. .
- 385 [Archana ()] *In vivo evaluation of chitosan-PVP-titanium dioxide nanocomposite as wound dressing material.*
386 *Carbohydrate Polymers*, D Archana . 2013. 95 p. .
- 387 [Younes ()] ‘Influence of acetylation degree and molecular weight of homogeneous chitosans on antibacterial and
388 antifungal activities’. I Younes . *International Journal of Food Microbiology* 2014. 185 p. .
- 389 [Hamouda ()] *Intranasal Immunization of Ferrets with Commercial Trivalent Influenza Vaccines Formulated in*
390 *a Nanoemulsion-Based Adjuvant. Clinical and vaccine immunology : CVI*, T Hamouda . 2011. 18 p. .
- 391 [Moongkarndi et al. ()] *Journal of veterinary diagnostic investigation: official publication of the American*
392 *Association of Veterinary Laboratory Diagnosticians, Inc*, P Moongkarndi , E Rodpai , S Kanarat . 2011.
393 23 p. . (Evaluation of an immunochromatographic assay for rapid detection of Salmonella enterica serovars
394 Typhimurium and Enteritidis)
- 395 [Mcdaniel and Browning ()] *Journal of wound, ostomy, and continence nursing : official publication of The*
396 *Wound, Ostomy and Continence Nurses Society*, J C Mcdaniel , K K Browning . 2014. 41 p. . (Smoking,
397 chronic wound healing, and implications for evidence-based practice)
- 398 [Chandika et al. ()] ‘Marinederived biological macromolecule-based biomaterials for wound healing and skin
399 tissue regeneration’. P Chandika , S.-C Ko , W.-K Jung . *International journal of biological macromolecules*
400 2015. p. 77.
- 401 [Erskine et al. ()] *Mastitis therapy and pharmacology. Veterinary Clinics of North America: Food Animal*
402 *Practice*, R J Erskine , S Wagner , F J Degraives . 2003. 19 p. .
- 403 [Niska ()] ‘Metal nanoparticles in dermatology and cosmetology: Interactions with human skin cells’. K Niska .
404 *Chemico-Biological Interactions* 2017. 295.
- 405 [Rolfe] *Micro-and Nanosensors for Medical and Biological Measurement. Optoelectronics, Instrumentation and*
406 *Data Processing*, P Rolfe .
- 407 [Bajpai et al. ()] ‘Moderate Intensity Static Magnetic Field has Bactericidal Effect on E. Coli and S. Epidermidis
408 on Sintered Hydroxyapatite’. I Bajpai , N Saha , B Basu . *Journal of biomedical materials research. Part B,*
409 *Applied biomaterials* 2012. 100 p. .
- 410 [Kalashnikova et al. ()] ‘Nanomaterials for wound healing: scope and advancement’. I Kalashnikova , S Das , S
411 Seal . *Nanomedicine* 2015. (10) p. .

- 412 [Yin ()] 'Nanoparticle-based bio-barcode assay for the detection of bluetongue virus'. H.-Q Yin . *Journal of*
413 *virological methods* 2011. 178 p. .
- 414 [Scott ()] *Nanoscience in Veterinary Medicine. Veterinary research communications*, N Scott . 2007. p. . (Suppl)
- 415 [Tocco ()] 'Nanotechnology-Based Therapies for Skin Wound Regeneration'. I Tocco . *Journal of Nanomaterials*
416 2012. 2012. p. 714134.
- 417 [Arenal and Molento ()] *Nanotechnology: Meeting the future of Veterinary Parasitology Research. Pesquisa*
418 *Veterinária Brasileira*, A Arenal , M Molento . 2015. 35 p. .
- 419 [Danesh-Bahreini ()] 'Nanovaccine for leishmaniasis: preparation of chitosan nanoparticles containing Leish-
420 mania superoxide dismutase and evaluation of its immunogenicity in BALB/c mice'. M Danesh-Bahreini .
421 *International journal of nanomedicine* 2011. 6 p. .
- 422 [Cuero et al. ()] 'Ncarboxymethylchitosan inhibition of aflatoxin production: Role of zinc'. R G Cuero , G Osuji
423 , A Washington . *Biotechnology Letters* 1991. 13 (6) p. .
- 424 [Chang ()] *pH Effects on solubility, zeta potential, and correlation between antibacterial activity and molecular*
425 *weight of chitosan. Carbohydrate Polymers*, S.-H Chang . 2015. 134 p. .
- 426 [Kumar and Koh ()] 'Physiochemical and optical study of chitosan-terephthaldehyde derivative for biomedical
427 applications'. S Kumar , J Koh . *International Journal of Biological Macromolecules* 2012. 51 (5) p. .
- 428 [Senel and McClure ()] *Potential applications of chitosan in veterinary medicine. Advanced drug delivery reviews*,
429 S Senel , S McClure . 2004. 56 p. .
- 430 [Prasher et al. ()] P Prasher , M Singh , H Mudila . *Silver nanoparticles as antimicrobial therapeutics: current*
431 *perspectives and future challenges. 3 Biotech*, 2018. 8 p. 411.
- 432 [Qi ()] 'Preparation and antibacterial activity of chitosan nanoparticles'. L Qi . *Carbohydrate Research* 2004. 339
433 (16) p. .
- 434 [Swain ()] *Preparation and effects of nano mineral particle feeding in livestock: A review. Veterinary World*, P
435 Swain . 2015. 8 p. 888.
- 436 [Russo ()] 'Preparation, characterization and in vitro antiviral activity evaluation of foscarnet-chitosan nanopar-
437 ticles'. E Russo . *Colloids and Surfaces B: Biointerfaces* 2014. 118 p. .
- 438 [Seegers et al. ()] *Production effects related to mastitis and mastitis economics in dairy cattle herds. Veterinary*
439 *research*, H Seegers , C Fourichon , F Beaudeau . 2003. 34 p. .
- 440 [Lee ()] *Quality and safety aspects of meat products as affected by various physical manipulations of packaging*
441 *materials. Meat science*, K.-T Lee . 2010. 86 p. .
- 442 [Rabea] E Rabea . *Chitosan as Antimicrobial Agent: Applications and Mode of Action*,
- 443 [Neethirajan ()] 'Recent advancement in biosensors technology for animal and livestock health management'. S
444 Neethirajan . *Biosensors and Bioelectronics* 2017. 98 p. .
- 445 [Zhu ()] 'Recent developments in antibodybased assays for the detection of bacterial toxins'. K Zhu . *Toxins*
446 2014. 6 (4) p. .
- 447 [B?kowski ()] 'Silver and Zinc Nanoparticles in Animal Nutrition-A Review'. M B?kowski . *Annals of Animal*
448 *Science* 2018. 18 p. .
- 449 [Lansdown ()] *Silver in health care: antimicrobial effects and safety in use. Current problems in dermatology*, A
450 B G Lansdown . 2006. 33 p. .
- 451 [Ojeda-Martínez ()] 'Skin wound healing with chitosan thin films containing supported silver nanospheres'. M L
452 Ojeda-Martínez . *Journal of Bioactive and Compatible Polymers* 2015. 30 (6) p. .
- 453 [Gamboa ()] 'Spray Freeze-Drying as an Alternative to the Ionic Gelation Method to Produce Chitosan and
454 Alginate Nano-Particles Targeted to the Colon'. A Gamboa . *Journal of pharmaceutical sciences* 2015. 104.
- 455 [Ratajska ()] *Studies on the biodegradation of chitosan in an aqueous medium. Fibres and Textiles in Eastern*
456 *Europe*, M Ratajska . 2003. 11 p. .
- 457 [George ()] 'Surface defects on plate-shaped silver nanoparticles contribute to its hazard potential in a fish gill
458 cell line and zebrafish embryos'. S George . *ACS nano* 2012. 6 (5) p. .
- 459 [Zhong ()] 'Synthesis of acyl thiourea derivatives of chitosan and their antimicrobial activities in vitro'. Z Zhong
460 . *Carbohydrate Research* 2008. 343 (3) p. .
- 461 [Maree ()] 'Synthesis of empty african horse sickness virus particles'. S Maree . *Virus Research* 2016. 213 p. .
- 462 [Rizeq ()] *Synthesis, bioapplications, and toxicity evaluation of chitosan-based nanoparticles. International*
463 *journal of molecular sciences*, B R Rizeq . 2019. 20 p. 5776.
- 464 [Lin ()] 'Techniques for physicochemical characterization of nanomaterials'. P.-C Lin . *Biotechnology advances*
465 2014. 32 (4) p. .

- 466 [Joanitti and Silva ()] *The Emerging Potential of By-Products as Platforms for Drug Delivery Systems. Current*
467 *drug targets*, G Joanitti , L Silva . 2013.
- 468 [Byrd et al. ()] 'The human skin microbiome'. A L Byrd , Y Belkaid , J A Segre . *Nature Reviews Microbiology*
469 2018. 16 (3) p. 143.
- 470 [Bai ()] 'Theranostics Aspects of Various Nanoparticles in Veterinary Medicine. International journal of molecular
471 sciences'. D.-P Bai . 58. *Din, N., EFFECTS OF DIETARY NANO-ZINC AND NANO-SELENIUM*
472 *ADDITION ON PRODUCTIVE AND PHYSIOLOGICAL PERFORMANCE OF GROWING RABBITS*
473 *AT FATTENING PERIOD. Egyptian Journal of Nutrition and Feeds* 2018. 2019. 19 (11) p. .
- 474 [Grz?bka-Zasadzi?ska et al. ()] 'Thermal and mechanical properties of chitosan nanocomposites with cellulose
475 modified in ionic liquids'. A Grz?bka-Zasadzi?ska , T Amietszajew , S Borysiak . *Journal of Thermal Analysis*
476 *and Calorimetry* 2017. 130 (1) p. .
- 477 [Garcia ()] 'Towards development of a dermal rudiment for enhanced wound healing response'. Y Garcia .
478 *Biomaterials* 2008. 29 (7) p. .
- 479 [Bilgili ()] 'Use Areas of Nanotechnology in Veterinary Medicine'. A Bilgili , M . *Journal of Food Science and*
480 *Engineering* 2019. 9.
- 481 [Martin ()] 'Wound Healing–Aiming for Perfect Skin Regeneration'. P Martin . *Science* 1997. 276 (5309) p. .
- 482 [Gurtner ()] 'Wound repair and regeneration'. G C Gurtner . *Nature* 2008. 453 (7193) p. .
- 483 [Reinke and Sorg ()] 'Wound repair and regeneration. European surgical research'. J M Reinke , H Sorg .
484 *Europaische chirurgische Forschung. Recherches chirurgicales europeennes* 2012. 49 (1) p. .
- 485 [Eming et al. ()] *Wound repair and regeneration: mechanisms, signaling, and translation. Science translational*
486 *medicine*, S A Eming , P Martin , M Tomic-Canic . 2014. 6 p. .
- 487 [Metwally] 'Wound-Healing Activity of Green and Chemical Zinc Oxide Nanoparticles (ZnO-NPs) Gels in Equine
488 Wounds: A clinical Study'. A Metwally . *SVU-International Journal of Veterinary Sciences* 2020 (1) p. .
- 489 [Manuja ()] 'Zinc Oxide Nanoparticles: Opportunities and Challenges in Veterinary Sciences'. A Manuja .
490 *Immunome Research* 2015. (11) .